

(19) World Intellectual Property Organization
International Bureau



(43) International Publication Date
20 June 2002 (20.06.2002)

PCT

(10) International Publication Number
WO 02/48301 A1

(51) International Patent Classification⁷: C11D 3/16, 3/39,
C07D 471/08, 487/04, 487/08 // (C07D 471/08, 223:00,
221:00) (C07D 487/04, 209:00, 209:00) (C07D 487/08,
223:00, 223:00) (C07D 487/08, 245:00, 225:00)

(21) International Application Number: PCT/EP01/13314

(22) International Filing Date:
15 November 2001 (15.11.2001)

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:
0030673.8 15 December 2000 (15.12.2000) GB

(71) Applicant (for AE, AG, AU, BB, BZ, CA, CY, GB, GD, GH,
GM, IE, IL, KE, LC, LK, LS, MN, MW, NZ, SD, SG, SL, SZ,
TT, TZ, UG, ZA, ZW only): UNILEVER PLC [GB/GB];
Unilever House, Blackfriars, London EC4P 4BQ (GB).

(71) Applicant (for AL, AM, AT, AZ, BA, BE, BG, BR, BY, CH,
CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, ES, FI,
FR, GE, GR, HR, HU, ID, IS, IT, JP, KG, KP, KR, KZ, LR,
LT, LU, LV, MA, MC, MD, MG, MK, MX, MZ, NL, NO, PH,
PL, PT, RO, RU, SE, SI, SK, TJ, TM, TR, UA, UZ, VN, YU
only): UNILEVER NV [NL/NL]; Weena 455, NL-3013
AL Rotterdam (NL).

(71) Applicant (for IN only): HINDUSTAN LEVER LIM-
ITED [IN/IN]; Hindustan Lever House, 165/166 Backbay
Reclamation, Maharashtra, 400 020 Mumbai (IN).

(72) Inventors: BOERZEL, Heidi; 64B Revere Street,
Boston, MA 02114 (US). COMBA, Peter; University of
Heidelberg, Anorganisch-Chemisches Institut, Im Neuen-
heimer Feld 270, 69120 Heidelberg (DE). HAGE, Ronald;

Unilever Research Vlaardingen, Olivier van Noortlaan
120, NL-3133 AT Vlaardingen (NL). KERSCHER, Mar-
ion; University of Heidelberg, Anorganisch-Chemisches
Institut, Im Neuenheimer Feld 270, 69120 Heidelberg
(DE). LIENKE, Joachim; Unilever Research Vlaardin-
gen, Olivier van Noortlaan 120, NL-3133 AT Vlaardingen
(NL). MERZ, Michael; University of Heidelberg, Anor-
ganisch-Chemisches Institut, Im Neuenheimer Feld 270,
69120 Heidelberg (DE).

(74) Agents: ELLIOTT, Peter, William et al.; Unilever PLC,
Patent Department, Colworth House, Sharnbrook, Bedford,
Bedfordshire MK44 1LQ (GB).

(81) Designated States (national): AE, AG, AL, AM, AT, AU,
AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CO, CR, CU,
CZ, DE, DK, DM, DZ, EC, EE, ES, FI, GB, GD, GE, GH,
GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC,
LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW,
MX, MZ, NO, NZ, PH, PL, PT, RO, RU, SD, SE, SG, SI,
SK, SL, TJ, TM, TR, TT, TZ, UA, UG, UZ, VN, YU, ZA,
ZW.

(84) Designated States (regional): ARIPO patent (GH, GM,
KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZM, ZW),
Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM),
European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR,
GB, GR, IE, IT, LU, MC, NL, PT, SE, TR); OAPI patent
(BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR,
NE, SN, TD, TG).

Published:

- with international search report
- before the expiration of the time limit for amending the
claims and to be republished in the event of receipt of
amendments

For two-letter codes and other abbreviations, refer to the "Guid-
ance Notes on Codes and Abbreviations" appearing at the begin-
ning of each regular issue of the PCT Gazette.

(54) Title: LIGAND AND COMPLEX FOR CATALYTICALLY BLEACHING A SUBSTRATE

(57) Abstract: The present invention relates to a bleaching composition comprising: a) a monomer ligand or transition metal cat-
alyst thereof of a ligand having the formula (I); wherein each R is independently hydrogen, F, Cl, Br, hydroxyl, C1-C4-alkylo-,
-NH-CO-H, -NH-CO-C1-C4-alkyl, -NH2, -NH-C1-C4-alkyl, and C1-C4-alkyl; R1 and R2 are independently selected from: C1-C4-
alkyl, C6-C10-aryl, and, a group containing a heteroatom capable of coordinating to a transition metal, wherein at least one of
R1 and R2 is the group containing the heteroatom; R3 and R4 are independently selected from hydrogen, C1-C8 alkyl, C1-C8-
alkyl-O-C1-C8-alkyl, C1-C8-alkyl-O-C6-C10-aryl, C6-C10-aryl, C1-C8-hydroxyalkyl, and -(CH2)_nC(O)OR5 wherein R5 is inde-
pendently selected from: hydrogen, C1-C4-alkyl, n is from 0 to 4, and mixtures thereof; and, X is selected from C=O, -[C(R6)2]_n-
wherein Y is from 0 to 3, each R6 is independently selected from hydrogen, hydroxyl, C1-C4-alkoxy, C1-C4-alkyl; and b) the bal-
ance carriers and adjunct ingredient.

- 1 -

LIGAND AND COMPLEX FOR CATALYTICALLY BLEACHING A SUBSTRATEFIELD OF INVENTION

This invention relates to a class of ligand or complex
5 thereof useful as catalysts for catalytically bleaching
substrates with atmospheric oxygen.

BACKGROUND OF INVENTION

The use of bleaching catalysts for stain removal has been
10 developed over recent years. The recent discovery that some
catalysts are capable of bleaching effectively in the
absence of an added peroxy source has recently become the
focus of some interest, for example: WO9965905; WO0012667;
WO0012808; and, WO0029537.


15

The search for new classes of compounds that are suitable as
air bleaching catalyst is ongoing.

Various [3.3.1] bicyclo compounds and complexes thereof are
20 discussed in the literature, see for example: Comba P. et
al., J. Chem. Soc. Dalton Trans, 1998, (23) 3997-4001;
Börzel et al. Chem. Eur. J. 1999, 5, No. 6, 1716 to 1721 and
review by P. Comba in Coordination Chemistry Reviews 2000,
200-202, 217 to 245, entitled "Coordination compounds in the
25 Entactic State". These compounds are discussed in terms of
their physical properties.

WO0060045 discloses a bleaching system comprising: a) from
about 1ppb, by weight of a transition metal catalyst
30 comprising: i) a transition metal; ii) a ligand having
formula (I):

- 2 -



wherein each R is independently hydrogen, hydroxyl, C1-C4
 5 alkyl, and mixtures thereof; R1 is C1-C4 alkyl, C6-C10 aryl,
 and mixtures thereof; R2 is C1-C4 alkyl, C6-C10 aryl, and
 mixtures thereof; R3 and R4 are each independently hydrogen,
 C1-C8 alkyl, C1-C8 hydroxyalkyl, $-(CH_2)_xCO_2R_5$ wherein R5 is
 C1-C4 alkyl, x is from 0 to 4, and mixtures thereof; X is
 10 carbonyl, $-C(R_6)_2-$ wherein each R6 is independently
 hydrogen,
 hydroxyl, C1-C4 alkyl, and mixtures thereof; b) optionally a
 source of hydrogen peroxide; and c) the balance carriers and
 adjunct ingredients. However, the teaching of WO0060045
 15 limits substituents at the nitrogens (3 and 7 positions) of
 bicyclostructure to homoaromatic carbon groups, namely alkyl
 and aryl.

SUMMARY OF INVENTION

20 We have found that the presence of a group bearing a
 heteroatom on one or more of the nitrogens of the
 bicyclostructure provides an enhanced activity. The
 compounds provided are surprisingly active as air bleaching
 catalysts. In addition, we also found that similar
 25 compounds are surprisingly active and provide novel ligands


- 3 -

and transition metal complexes thereof for use in air bleaching.

Accordingly, in a first aspect, the present invention provides a bleaching composition comprising:

A bleaching composition comprising:

- a) a monomer ligand or transition metal catalyst thereof of a ligand having the formula (I):



wherein each R is independently selected from: hydrogen, F, Cl, Br, hydroxyl, C1-C4-alkyl-O-, -NH-CO-H, -NH-CO-C1-C4-alkyl, -NH2, -NH-C1-C4-alkyl, and C1-C4-alkyl;

R1 and R2 are independently selected from:

C1-C4-alkyl,

C6-C10-aryl, and,

a group containing a heteroatom capable of coordinating to a transition metal, wherein at least one of R1 and R2 is the group containing the heteroatom;

R3 and R4 are independently selected from hydrogen, C1-C8 alkyl, C1-C8-alkyl-O-C1-C8-alkyl, C1-C8-alkyl-O-C6-C10-aryl,

C6-C10-aryl, C1-C8-hydroxyalkyl, and $-(CH_2)_nC(O)OR_5$

- 4 -

wherein R5 is independently selected from: hydrogen, C1-C4-alkyl, n is from 0 to 4, and mixtures thereof; and, X is selected from C=O, $-[C(R6)_2]_Y-$ wherein Y is from 0 to 3 each R6 is independently selected from hydrogen, hydroxyl, C1-C4-alkoxy and C1-C4-alkyl; and,

b) the balance carriers and adjunct ingredients.

Preferred groups containing the heteroatom may be found in a heterocycloalkyl: selected from the group consisting of: pyrrolinyl; pyrrolidinyl; morpholinyl; piperidinyl; piperazinyl; hexamethylene imine; 1,4-piperazinyl; tetrahydrothiophenyl; tetrahydrofuranyl; tetrahydropyranyl; and oxazolidinyl, wherein the heterocycloalkyl may be connected to the ligand via any atom in the ring of the selected heterocycloalkyl, a -C1-C6-alkyl-heterocycloalkyl, wherein the heterocycloalkyl of the -C1-C6-heterocycloalkyl is selected from the group consisting of: piperidinyl; piperidine; 1,4-piperazine, tetrahydrothiophene; tetrahydrofuran; pyrrolidine; and tetrahydropyran, wherein the heterocycloalkyl may be connected to the -C1-C6-alkyl via any atom in the ring of the selected heterocycloalkyl, a -C1-C6-alkyl-heteroaryl, wherein the heteroaryl of the -C1-C6-alkylheteroaryl is selected from the group consisting of: pyridinyl; pyrimidinyl; pyrazinyl; triazolyl; pyridazinyl; 1,3,5-triazinyl; quinolinyl; isoquinolinyl; quinoxalinyl; imidazolyl; pyrazolyl; benzimidazolyl; thiazolyl; oxazolidinyl; pyrrolyl; carbazolyl; indolyl; and isoindolyl, wherein the heteroaryl may be connected to the -C1-C6-alkyl via any atom in the ring of the selected

- 5 -

heteroaryl and the selected heteroaryl is optionally substituted by -C1-C4-alkyl,
a -C0-C6-alkyl-phenol or thiophenol,
a -C2-C4-alkyl-thiol, thioether or alcohol,
5 a -C2-C4-alkyl-amine, and
a -C2-C4-alkyl-carboxylate.

In a second aspect, the present invention provides a bleaching composition comprising, in an aqueous medium,
10 atmospheric oxygen and a bicyclo ligand of the general Formula (I) which forms a complex with a transition metal, the complex catalysing bleaching of a substrate by the atmospheric oxygen, wherein the aqueous medium is substantially devoid of peroxygen bleach or a peroxy-based
15 or -generating bleach system. It is preferred that the medium has a pH value in the range from pH 6 to 11 and most preferably from pH 8 to 10.

The present invention also provides novel compounds of the
20 general Formula (I) with the proviso that the following compounds are excluded:
dimethyl 2,4-di-(2-pyridyl)-3,7-bis-(pyridin-2-ylmethyl)-3,7-diaza-bicyclo[3.3.1]nonan-9-one-1,5-dicarboxylate;
1,5-bis-(hydroxymethylene)-2,4-di-(2-pyridyl)-3,7-bis-(pyridin-2-ylmethyl)-3,7-diazabicyclo[3.3.1]nonan-9-ol;
25 dimethyl 2,4-di-(2-pyridyl)-3,7-bis-(pyridin-2-ylethyl)-3,7-diaza-bicyclo[3.3.1]nonan-9-one-1,5-dicarboxylate;
dimethyl 2,4-di-(2-pyridyl)-3-(5-carboxypentyl)-7-methyl-3,7-diaza-bicyclo[3.3.1]nonan-9-one-1,5-dicarboxylate;
30 dimethyl 2,4-di-(2-pyridyl)-3-(2-methoxyethyl)-7-methyl-3,7-diaza-bicyclo[3.3.1]nonan-9-one-1,5-dicarboxylate; diethyl-

- 6 -

2,4-dipyridyl-7-picolyl-3,7-diaza-bicyclo-[3.3.1]-nonan-9-one-1,5-dicarboxylate; diethyl-2,4-dipyridyl-7-benzyl-3-hydroxyethyl-3,7-diaza-bicyclo-[3.3.1]-nonan-9-one-1,5-dicarboxylate; and, dimethyl-2,4-dipyridyl-7-benzyl-3-hydroxyethyl-3,7-diaza-bicyclo-[3.3.1]-nonan-9-one-1,5-dicarboxylate.

An advantage of the class of ligand and complex according to the present invention is that the complex can catalyse
10 bleaching of a substrate by atmospheric oxygen, thus permitting its use in a medium such as an aqueous medium that is substantially devoid of peroxygen bleach or a peroxy-based or -generating bleach system. We have also found that complexes of this class are surprisingly
15 effective in catalysing bleaching of the substrate by atmospheric oxygen after treatment of the substrate. The composition of the present invention bleaches a substrate with at least 10 %, preferably at least 50 % and optimally at least 90 % of any bleaching of the substrate being
20 effected by oxygen sourced from the air.

One skilled in the art will appreciate that not all peroxy activating catalysts are capable of functioning as an oxygen activation catalyst. However, the converse is not true.
25 There is no evidence to indicate that any oxygen activation catalyst will not function as peroxy activating catalyst. In this regard, all oxygen activation catalysts disclosed herein may be used as a peroxy activating catalyst. Catalysts of the present invention may be incorporated into
30 a composition together with a peroxy species or source thereof. For a discussion of acceptable ranges of a peroxy

- 7 -

species or source thereof and other adjuvants that may be present the reader is directed to United States Patent 6,022,490, the contents of which are incorporated by reference.

5

The present invention extends to a method of bleaching a substrate comprising applying to the substrate, in an aqueous medium, the bleaching composition according to the present invention.

10

The present invention extends to a commercial package comprising the bleaching composition according to the present invention together with instructions for its use.

15 The present invention further provides a dry textile having an organic substance as defined above applied or deposited thereon, whereby bleaching by atmospheric oxygen is catalysed on the textile.

20 Advantageously, by enabling a bleaching effect even after the textile has been treated, the benefits of bleaching can be prolonged on the textile. Furthermore, since a bleaching effect is conferred to the textile after the treatment, the treatment itself, such as a laundry wash cycle, may for
25 example be shortened. Moreover, since a bleaching effect is achieved by atmospheric oxygen after treatment of the textile, hydrogen peroxide or peroxy-based bleach systems can be omitted from the treatment substance.

30 The organic substance may be contacted to the textile fabric in any suitable manner. For example, it may be applied in

- 8 -

dry form, such as in powder form, or in a liquor that is then dried, for example as an aqueous spray-on fabric treatment fluid or a wash liquor for laundry cleaning, or a non-aqueous dry cleaning fluid or spray-on aerosol fluid.

5 Other suitable means of contacting the organic substance to the textile may be used, as further explained below.

Any suitable textile that is susceptible to bleaching or one that one might wish to subject to bleaching may be used.

10 Preferably the textile is a laundry fabric or garment.

In a preferred embodiment, the method according to the present invention is carried out on a laundry fabric using an aqueous treatment liquor. In particular, the treatment
15 may be effected in a wash cycle for cleaning laundry. More preferably, the treatment is carried out in an aqueous detergent bleach wash liquid.

In a preferred embodiment, the treated textile is dried, by
20 allowing it to dry under ambient temperature or at elevated temperatures. The elevated temperatures are commonly provided by a heated agitated environment, as for example found in a tumble dryer, which has been found to accelerate and enhance the air bleaching effect.

25 The bleaching method may be carried out by simply leaving the substrate in contact with the organic substance for a sufficient period of time. Preferably, however, the organic substance is in an aqueous medium, and the aqueous medium on
30 or containing the substrate is agitated.

- 9 -

The organic substance can be contacted with the textile fabric in any conventional manner. For example it may be applied in dry form, such as in powder form, or in a liquor that is then dried, for example in an aqueous spray-on
5 fabric treatment fluid or a wash liquor for laundry cleaning, or a non-aqueous dry cleaning fluid or spray-on aerosol fluid.

In a preferred embodiment, the treated textile is dried, by
10 allowing it to dry under ambient temperature or at elevated temperatures.

In a particularly preferred embodiment the method according to the present invention is carried out on a laundry fabric
15 using aqueous treatment liquor. In particular the treatment may be effected in, or as an adjunct to, an essentially conventional wash cycle for cleaning laundry. More preferably, the treatment is carried out in an aqueous detergent wash liquor. The organic substance can be
20 delivered into the wash liquor from a powder, granule, pellet, tablet, block, bar or other such solid form. The solid form can comprise a carrier, which can be particulate, sheet-like or comprise a three-dimensional object. The carrier can be dispersible or soluble in the wash liquor or
25 may remain substantially intact. In other embodiments, the organic substance can be delivered into the wash liquor from a paste, gel or liquid concentrate.

It is particularly advantageous that the organic substance
30 used in the method of the present invention makes use of atmospheric oxygen in its bleaching activity. This avoids

- 10 -

the requirement that peroxygen bleaches and/or other relatively large quantities of reactive substances need be used in the treatment process. Consequently, only a relatively small quantity of bleach active substance need be
5 employed and this allows dosage routes to be exploited that could previously not be used. Thus, while it is preferable to include the organic substance in a composition that is normally used in a washing process, such as a pre-treatment, main-wash, conditioning composition or ironing aid, other
10 means for ensuring that the organic substance is present in the wash liquor may be envisaged.

For example, it is envisaged that the organic substance can be presented in the form of a body from which it is slowly
15 released during the whole or part of the laundry process. Such release can occur over the course of a single wash or over the course of a plurality of washes. In the latter case it is envisaged that the organic substance can be released from a carrier substrate used in association with the wash
20 process, e.g. from a body placed in the dispenser drawer of a washing machine, elsewhere in the delivery system or in the drum of the washing machine. When used in the drum of the washing machine the carrier can be freely moving or fixed relative to the drum. Such fixing can be achieved by
25 mechanical means, for example by barbs that interact with the drum wall, or employ other forces, for example a magnetic force. The modification of a washing machine to provide for means to hold and retain such a carrier is envisaged similar means being known from the analogous art
30 of toilet block manufacture. Freely moving carriers such as shuttles for dosage of surfactant materials and/or other

- 11 -

detergent ingredients into the wash can comprise means for the release of the organic substance into the wash.

In the alternative, the organic substance can be presented
5 in the form of a wash additive that preferably is soluble. The additive can take any of the physical forms used for wash additives, including powder, granule, pellet, sheet, tablet, block, bar or other such solid form or take the form of a paste, gel or liquid. Dosage of the additive can be
10 unitary or in a quantity determined by the user. While it is envisaged that such additives can be used in the main washing cycle, the use of them in the conditioning or drying cycle is not hereby excluded.

15 The present invention is not limited to those circumstances in which a washing machine is employed, but can be applied where washing is performed in some alternative vessel. In these circumstances it is envisaged that the organic substance can be delivered by means of slow release from the
20 bowl, bucket or other vessel which is being employed, or from any implement which is being employed, such as a brush, bat or dolly, or from any suitable applicator.

Suitable pre-treatment means for application of the organic
25 substance to the textile material prior to the main wash include sprays, pens, roller-ball devices, bars, soft solid applicator sticks and impregnated cloths or cloths containing microcapsules. Such means are well known in the analogous art of deodorant application and/or in spot
30 treatment of textiles. Similar means for application are employed in those embodiments where the organic substance is

- 12 -

applied after the main washing and/or conditioning steps have been performed, e.g. prior to or after ironing or drying of the cloth. For example, the organic substance may be applied using tapes, sheets or sticking plasters coated
5 or impregnated with the substance, or containing microcapsules of the substance. The organic substance may for example be incorporated into a drier sheet so as to be activated or released during a tumble-drier cycle, or the substance can be provided in an impregnated or microcapsule-
10 containing sheet so as to be delivered to the textile when ironed.

Many transition metal complexes have high extinction coefficients in the visible. In this regard, use over time
15 may result in some colour deposition on a substrate after repeated washing. The addition of a limited amount of a peroxy source serves to reduce colour deposition in those instances in which it occurs whilst still permitting air bleaching. Nevertheless, we have found that in certain
20 instances the free ligand may be used in the bleaching composition of the present invention. By using a free ligand, a bleaching formulation may be prepared that is consistent with consumer formulation colour expectation. In such a formulation the metal ion may be provided by the
25 composition or by trace metals found in the stain.

DETAILED DESCRIPTION OF THE INVENTION

The ligand as described herein is capable of dynamic inversion. The ability of the ligand to chelate to a TM
30 depends upon the stereochemistry of the substituents. It is preferred that substituents are endo-endo, but it is likely

- 13 -

that stereochemical conversion takes place by retro-Mannich conversion. Retro-Mannich may be prevented by changing the groups present such that retro-Mannich reactions are unfavoured. Nevertheless, it is likely that endo-exo and
5 exo-exo ligands as described herein coordinate to transition metal ions in many instances and are capable of functioning as air bleaching catalysts.

Referring to ligands and complexes thereof and bleaching
10 compositions derived therefrom with respect to Formula (I), it is preferred that each R is the same; and $R_3 = R_4$, and more preferred that R_3 and R_4 are the same and are -
(CH₂)_nC(O)O-C1-C4-alkyl. It is even more preferred that R_3 and R_4 are selected from the group consisting of -CH₂OH, -
15 C(O)O-C1-C6-alkyl, and phenyl.

Referring to X, it is preferred that Y = 1, and most preferred wherein X is C=O.

20 It is preferred that at least one of R_1 and R_2 is a 3-C0-C6-alkyl-pyridin-2-yl-C0-C6-alkyl. It is most preferred that at least one of R_1 and R_2 is selected from the group consisting of: 3-ethyl-pyridin-2-ylmethyl, pyridin-2-ylmethyl, 3-methyl-pyridin-2-ylmethyl, and 6-amide-pyridin-2-ylmethyl,
25 of which pyridin-2-ylmethyl is preferred from this group. It is even more preferred that both R_1 and R_2 are selected from this group.

The catalyst may be used as a preformed complex of the
30 ligand and a transition metal. Alternatively, the catalyst may be formed from the free ligand that complexes with a

- 14 -

transition metal already present in the water or that complexes with a transition metal present in the substrate. The composition may also be formulated as a composition of the free ligand or a transition metal-substitutable metal-ligand complex, and a source of transition metal, whereby
 5 the complex is formed *in situ* in the medium.

The ligand forms a complex with one or more transition metals, in the latter case for example as a dinuclear
 10 complex. Suitable transition metals include for example: manganese in oxidation states II-V, iron II-V, copper I-III, cobalt I-III, titanium II-IV, tungsten IV-VI, vanadium II-V and molybdenum II-VI.

15 The ligand forms a complex of the general formula (A1):



in which:

20 M represents a metal selected from Mn(II)-(III)-(IV)-(V), Cu(I)-(II)-(III), Fe(II)-(III)-(IV)-(V), Co(I)-(II)-(III), Ti(II)-(III)-(IV), V(II)-(III)-(IV)-(V), Mo(II)-(III)-(IV)-(V)-(VI) and W(IV)-(V)-(VI), preferably selected from Fe(II)-(III)-(IV)-(V);

25 L represents a ligand as herein defined, or its protonated or deprotonated analogue;

X represents a coordinating species selected from any monò, bi or tri charged anions and any neutral molecules able to coordinate the metal in a mono, bi or tridentate
 30 manner, preferably selected from O^{2-} , RBO_2^{2-} , $RCOO^-$, $RCONR^-$, OH^- , NO_3^- , NO , S^{2-} , RS^- , PO_4^{3-} , PO_3OR^{3-} , H_2O , CO_3^{2-} , HCO_3^- , ROH ,

- 15 -

$N(R)_3$, ROO^- , O_2^{2-} , O_2^- , RCN , Cl^- , Br^- , OCN^- , SCN^- , CN^- , N_3^- , F^- ,
 I^- , RO^- , ClO_4^- , and $CF_3SO_3^-$, and more preferably selected from
 O^{2-} , RBO_2^{2-} , $RCOO^-$, OH^- , NO_3^- , S^{2-} , RS^- , PO_3^{4-} , H_2O , CO_3^{2-} , HCO_3^- ,
 ROH , $N(R)_3$, Cl^- , Br^- , OCN^- , SCN^- , RCN , N_3^- , F^- , I^- , RO^- , ClO_4^- ,
 5 and $CF_3SO_3^-$;

Y represents any non-coordinated counter ion,
 preferably selected from ClO_4^- , BR_4^- , $[MX_4]^-$, $[MX_4]^{2-}$, PF_6^- ,
 $RCOO^-$, NO_3^- , RO^- , $N^+(R)_4$, ROO^- , O_2^{2-} , O_2^- , Cl^- , Br^- , F^- , I^- ,
 $CF_3SO_3^-$, $S_2O_6^{2-}$, OCN^- , SCN^- , H_2O , RBO_2^{2-} , BF_4^- and BPh_4^- , and
 10 more preferably selected from ClO_4^- , BR_4^- , $[FeCl_4]^-$, PF_6^- ,
 $RCOO^-$, NO_3^- , RO^- , $N^+(R)_4$, Cl^- , Br^- , F^- , I^- , $CF_3SO_3^-$, $S_2O_6^{2-}$,
 OCN^- , SCN^- , H_2O and BF_4^- ;

a represents an integer from 1 to 10, preferably from 1
 to 4;

15 k represents an integer from 1 to 10;

n represents an integer from 1 to 10, preferably from 1
 to 4;

m represents zero or an integer from 1 to 20,
 preferably from 1 to 8; and

20 each R independently represents a group selected from
 hydrogen, hydroxyl, $-R'$ and $-OR'$, wherein R' = alkyl, alkenyl,
 cycloalkyl, heterocycloalkyl, aryl, heteroaryl or a carbonyl
 derivative group, R' being optionally substituted by one or
 more functional groups E, wherein E independently represents
 25 a functional group selected from $-F$, $-Cl$, $-Br$, $-I$, $-OH$, $-OR'$,
 $-NH_2$, $-NHR'$, $-N(R')_2$, $-N(R')_3^+$, $-C(O)R'$, $-OC(O)R'$, $-COOH$, $-COO^-$
 (Na^+, K^+) , $-COOR'$, $-C(O)NH_2$, $-C(O)NHR'$, $-C(O)N(R')_2$,
 heteroaryl, $-R'$, $-SR'$, $-SH$, $-P(R')_2$, $-P(O)(R')_2$, $-P(O)(OH)_2$,
 $-P(O)(OR')_2$, $-NO_2$, $-SO_3H$, $-SO_3^-(Na^+, K^+)$, $-S(O)_2R'$, $-NHC(O)R'$, and
 30 $-N(R')C(O)R'$, wherein R' represents cycloalkyl, aryl,

- 16 -

arylalkyl, or alkyl optionally substituted by -F, -Cl, -Br, -I, -NH₃⁺, -SO₃H, -SO₃⁻(Na⁺, K⁺), -COOH, -COO⁻(Na⁺, K⁺), -P(O)(OH)₂, or -P(O)(O⁻(Na⁺, K⁺))₂, and preferably each R independently represents hydrogen, optionally substituted
5 alkyl or optionally substituted aryl, more preferably hydrogen or optionally substituted phenyl, naphthyl or C₁₋₄-alkyl.

The counter ions Y in formula (A1) balance the charge z on
10 the complex formed by the ligand L, metal M and coordinating species X. Thus, if the charge z is positive, Y may be an anion such as RCOO⁻, BPh₄⁻, ClO₄⁻, BF₄⁻, PF₆⁻, RSO₃⁻, RSO₄⁻, SO₄²⁻, NO₃⁻, F⁻, Cl⁻, Br⁻, or I⁻, with R being hydrogen, optionally substituted alkyl or optionally substituted aryl.
15 If z is negative, Y may be a common cation such as an alkali metal, alkaline earth metal or (alkyl)ammonium cation.

Suitable counter ions Y include those which give rise to the formation of storage-stable solids. Preferred counter ions
20 for the preferred metal complexes are selected from R⁷COO⁻, ClO₄⁻, BF₄⁻, PF₆⁻, RSO₃⁻ (in particular CF₃SO₃⁻), RSO₄⁻, SO₄²⁻, NO₃⁻, F⁻, Cl⁻, Br⁻, and I⁻, wherein R represents hydrogen or optionally substituted phenyl, naphthyl or C₁-C₄ alkyl.

25 The novel compounds of Formula (I) as provided by the present invention also extend to their various transition metal complexes, the transition metal complexes are as discussed above with reference to (A1).

30 It will be appreciated that the complex (A1) can be formed by any appropriate means, including *in situ* formation

- 17 -

whereby precursors of the complex are transformed into the active complex of general formula (A1) under conditions of storage or use. Preferably, the complex is formed as a well-defined complex or in a solvent mixture comprising a salt of the metal M and the ligand L or ligand L-generating species. Alternatively, the catalyst may be formed *in situ* from suitable precursors for the complex, for example in a solution or dispersion containing the precursor materials. In one such example, the active catalyst may be formed *in situ* in a mixture comprising a salt of the metal M and the ligand L, or a ligand L-generating species, in a suitable solvent. Thus, for example, if M is iron, an iron salt such as FeSO_4 can be mixed in solution with the ligand L, or a ligand L-generating species, to form the active complex. Thus, for example, the composition may be formed from a mixture of the ligand L and a metal salt MX_n in which preferably $n=1-5$, more preferably 1-3. In another such example, the ligand L, or a ligand L-generating species, can be mixed with metal M ions present in the substrate or wash liquor to form the active catalyst *in situ*. Suitable ligand L-generating species include metal-free compounds or metal coordination complexes that comprise the ligand L and can be substituted by metal M ions to form the active complex according to the formula (A1).

25

The catalysts according to the present invention may be used for laundry cleaning, hard surface cleaning (including cleaning of lavatories, kitchen work surfaces, floors, mechanical ware washing etc.). As is generally known in the art, bleaching compositions are also employed in waste-water treatment, pulp bleaching during the manufacture of paper,

30

- 18 -

leather manufacture, dye transfer inhibition, food processing, starch bleaching, sterilisation, whitening in oral hygiene preparations and/or contact lens disinfection.

- 5 In typical washing compositions the level of the organic substance is such that the in-use level is from $1\mu\text{M}$ to 50mM , with preferred in-use levels for domestic laundry operations falling in the range 10 to $100\mu\text{M}$. Higher levels may be desired and applied in industrial bleaching processes, such as textile and paper pulp bleaching. These levels reflect the amount of catalyst that may be present in a wash dose of a detergent composition. The bleaching composition comprises at least 1 ppb of the ligand or complex thereof.
- 10
- 15 In the context of the present invention, bleaching should be understood as relating generally to the decolourisation of stains or of other materials attached to or associated with a substrate. However, it is envisaged that the present invention can be applied where a requirement is the removal and/or neutralisation by an oxidative bleaching reaction of malodours or other undesirable components attached to or otherwise associated with a substrate. Furthermore, in the context of the present invention bleaching is to be understood as being restricted to any bleaching mechanism or
- 20
- 25 process that does not require the presence of light or activation by light.


Synthesis

- In addition to the utility of the ligands and complexes of the present invention as catalysts another advantage is that the ligands are generally relatively easy to synthesise in
- 30

- 19 -


comparison to other ligands. The following is one example of a strategic synthetic approach; it will be evident to one skilled in the art of synthetic organic chemistry that many approaches may be taken to obtain ligands and complexes for use in the present invention. The ease of synthesis of the ligand of Formula (I) is dependent upon the nature of substituents about the structure. The ligands of Formula (I) are most preferably symmetric. Synthesis of these types of molecules are found in articles by U. Holzgrabe et al. in Arch. Pharm. (Weinheim, Ger.) 1992, 325, 657 and A. Samhammer et al. Arch. Pharm. (Weinheim, Ger.) 1984, 322, 557. Below is given a schematic example illustrating the ease of synthesis. The synthesis is shown in a two step synthesis, Scheme 1 and Scheme 2, but in some cases may be conducted as a "one-pot" synthesis depending upon the nature of the substituents. Nevertheless, where substituents R7 = R8 are different from R3 = R4 a two step synthesis is preferred. The product of reaction as found in Scheme 1 is referred to as dimethyl 2,6-di-(2-pyridyl)-1-methyl-piperid-4-one-3,5-dicarboxylate (NPy2), which can easily tautomerize to the enol. The synthesis is exemplified in R. Haller, K.W. Merz, *Pharm. Acta Helv.*, 1963, 442.

Scheme 1




- 20 -

Scheme 2



Another important intermediate that may be produced
 5 according to the general teachings of Scheme 1 wherein
 methylamine (CH_3NH_2) is replaced by 2-aminomethyl-pyridine
 such that a product referred to as dimethyl 2,6-di-(2-
 pyridyl)-1-(pyridin-2-ylmethyl)-piperid-4-one-3,5-
 dicarboxylate (NPy3) is produced, the structure of which is
 10 given below.




One skilled in the art will appreciate that whilst Ac [-
 CO(O)Me] is an electron withdrawing group and electron
 15 withdrawing groups are generally preferred to facilitate
 synthesis other groups will also allow the reaction to
 proceed. Examples of suitable electron withdrawing groups
 are given above and will be evident to one skilled in the
 art. The reaction is also driven by precipitation of the
 20 product from solution.

- 21 -

In instances, depending upon the nature of the substituents, for example a phenolic group, it will be necessary to protect certain functional groups. The choice of protecting groups during synthesis to prevent undesirable reactions will be evident to one skilled in the art. For a discussion of protecting groups in organic synthesis the reader is directed to T. W. Green and P. G. M. Wuts, Protective Groups In Organic Synthesis 3rd Ed.; J. Wiley and Sons, 1999.

It will be evident that if a diamine is substituted for methylamine in the reaction illustrated in Scheme 2 two structures may be linked together via the 7 positions as found in the structure below.



15

In addition, if a diamine is substituted for methylamine in the reaction illustrated in Scheme 1 a NPy2 structure is formed that is linked at the 3 positions. Obviously, this dimer would serve as a precursor to other dimer and polymer type structures. The present invention is confined to "monomer" ligands and not the dimer and polymer units linked by a covalent bond as described above. The term "monomer" as used herein is used to exclude these products in which covalently linked polyligand type structures are formed.

25

- 22 -

The Detergent Composition.

The air bleach catalyst and may be used in a detergent composition specifically suited for stain bleaching purposes, and this constitutes a second aspect of the invention. To that extent, the composition comprises a surfactant and optionally other conventional detergent ingredients. The invention in its second aspect provides an enzymatic detergent composition which comprises from 0.1 - 50 % by weight, based on the total detergent composition, of one or more surfactants. This surfactant system may in turn comprise 0 - 95 % by weight of one or more anionic surfactants and 5 to 100 % by weight of one or more nonionic surfactants. The surfactant system may additionally contain amphoteric or zwitterionic detergent compounds, but this is not normally desired owing to their relatively high cost. The enzymatic detergent composition according to the invention will generally be used as a dilution in water of about 0.05 to 2%.

In general, the nonionic and anionic surfactants of the surfactant system may be chosen from the surfactants described "Surface Active Agents" Vol. 1, by Schwartz & Perry, Interscience 1949, Vol. 2 by Schwartz, Perry & Berch, Interscience 1958, in the current edition of "McCutcheon's Emulsifiers and Detergents" published by Manufacturing Confectioners Company or in "Tenside-Taschenbuch", H. Stache, 2nd Edn., Carl Hauser Verlag, 1981.

Suitable nonionic detergent compounds which may be used include, in particular, the reaction products of compounds having a hydrophobic group and a reactive hydrogen atom, for

- 23 -

example, aliphatic alcohols, acids, amides or alkyl phenols with alkylene oxides, especially ethylene oxide either alone or with propylene oxide. Specific nonionic detergent compounds are C₆-C₂₂ alkyl phenol-ethylene oxide condensates, generally 5 to 25 EO, i.e. 5 to 25 units of ethylene oxide per molecule, and the condensation products of aliphatic C₈-C₁₈ primary or secondary linear or branched alcohols with ethylene oxide, generally 5 to 40 EO.

10 Suitable anionic detergent compounds which may be used are usually water-soluble alkali metal salts of organic sulphates and sulphonates having alkyl radicals containing from about 8 to about 22 carbon atoms, the term alkyl being used to include the alkyl portion of higher acyl radicals.

15 Examples of suitable synthetic anionic detergent compounds are sodium and potassium alkyl sulphates, especially those obtained by sulphating higher C₈-C₁₈ alcohols, produced for example from tallow or coconut oil, sodium and potassium alkyl C₉-C₂₀ benzene sulphonates, particularly sodium linear

20 secondary alkyl C₁₀-C₁₅ benzene sulphonates; and sodium alkyl glyceryl ether sulphates, especially those ethers of the higher alcohols derived from tallow or coconut oil and synthetic alcohols derived from petroleum. The preferred anionic detergent compounds are sodium C₁₁-C₁₅ alkyl benzene

25 sulphonates and sodium C₁₂-C₁₈ alkyl sulphates. Also applicable are surfactants such as those described in EP-A-328 177 (Unilever), which show resistance to salting-out, the alkyl polyglycoside surfactants described in EP-A-070 074, and alkyl monoglycosides.

- 24 -

Preferred surfactant systems are mixtures of anionic with nonionic detergent active materials, in particular the groups and examples of anionic and nonionic surfactants pointed out in EP-A-346 995 (Unilever). Especially preferred
5 is surfactant system that is a mixture of an alkali metal salt of a C₁₆-C₁₈ primary alcohol sulphate together with a C₁₂-C₁₅ primary alcohol 3-7 EO ethoxylate.

The nonionic detergent is preferably present in amounts
10 greater than 10%, e.g. 25-90% by weight of the surfactant system. Anionic surfactants can be present for example in amounts in the range from about 5% to about 40% by weight of the surfactant system.

15 The detergent composition may take any suitable physical form, such as a powder, granular composition, tablets, a paste or an anhydrous gel.

Enzymes

20 The detergent compositions of the present invention may additionally comprise one or more enzymes, which provide cleaning performance, fabric care and/or sanitation benefits.

25 Said enzymes include oxidoreductases, transferases, hydrolases, lyases, isomerases and ligases. Suitable members of these enzyme classes are described in Enzyme nomenclature 1992: recommendations of the Nomenclature Committee of the International Union of Biochemistry and Molecular Biology on
30 the nomenclature and classification of enzymes, 1992, ISBN 0-12-227165-3, Academic Press.

- 25 -

Examples of the hydrolases are carboxylic ester hydrolase, thiolester hydrolase, phosphoric monoester hydrolase, and phosphoric diester hydrolase which act on the ester bond;

5 glycosidase which acts on O-glycosyl compounds; glycosylase hydrolysing N-glycosyl compounds; thioether hydrolase which acts on the ether bond; and exopeptidases and endopeptidases which act on the peptide bond. Preferable among them are carboxylic ester hydrolase, glycosidase and exo- and

10 endopeptidases. Specific examples of suitable hydrolases include (1) exopeptidases such as aminopeptidase and carboxypeptidase A and B and endopeptidases such as pepsin, pepsin B, chymosin, trypsin, chymotrypsin, elastase, enteropeptidase, cathepsin B, papain, chymopapain, ficain,

15 thrombin, plasmin, renin, subtilisin, aspergillopepsin, collagenase, clostripain, kallikrein, gastricsin, cathepsin D, bromelain, chymotrypsin C, urokinase, cucumisin, oryzin, proteinase K, thermomycolin, thermitase, lactocepin, thermolysin, bacillolysin. Preferred among them is

20 subtilisin; (2) glycosidases such as α -amylase, β -amylase, glucoamylase, isoamylase, cellulase, endo-1,3(4)- β -glucanase (β -glucanase), xylanase, dextranase, polygalacturonase (pectinase), lysozyme, invertase, hyaluronidase, pullulanase, neopullulanase, chitinase, arabinosidase,

25 exocellobiohydrolase, hexosaminidase, mycodextranase, endo-1,4- β -mannanase (hemicellulase), xyloglucanase, endo- β -galactosidase (keratanase), mannanase and other saccharide gum degrading enzymes as described in WO-A-99/09127.

Preferred among them are α -amylase and cellulase; (3)

30 carboxylic ester hydrolase including carboxylesterase, lipase, phospholipase, pectinesterase, cholesterol esterase,

- 26 -

chlorophyllase, tannase and wax-ester hydrolase. Preferred among them is lipase.

Examples of transferases and ligases are glutathione S-
5 transferase and acid-thiol ligase as described in WO-A-98/59028 and xyloglycan endotransglycosylase as described in WO-A-98/38288.

Examples of lyases are hyaluronate lyase, pectate lyase,
10 chondroitinase, pectin lyase, alginase II. Especially preferred is pectolyase, which is a mixture of pectinase and pectin lyase.

Examples of the oxidoreductases are oxidases such as glucose
15 oxidase, methanol oxidase, bilirubin oxidase, catechol oxidase, laccase, peroxidases such as ligninase and those described in WO-A-97/31090, monooxygenase, dioxygenase such as lipoxygenase and other oxygenases as described in WO-A-99/02632, WO-A-99/02638, WO-A-99/02639 and the
20 cytochrome based enzymatic bleaching systems described in WO-A-99/02641.

The activity of oxidoreductases, in particular the phenol
oxidising enzymes in a process for bleaching stains on
25 fabrics and/or dyes in solution and/or antimicrobial treatment can be enhanced by adding certain organic compounds, called enhancers. Examples of enhancers are 2,2'-azo-bis-(3-ethylbenzo-thiazoline-6-sulphonate (ABTS) and Phenothiazine-10-propionate (PTP). More enhancers are
30 described in WO-A-94/12619, WO-A-94/12620 , WO-A-94/12621, WO-A-97/11217, WO-A-99/23887. Enhancers are generally added

- 27 -

at a level of 0.01% to 5% by weight of detergent composition.

Builders, polymers and other enzymes as optional ingredients
5 may also be present as found in WO0060045.

Suitable detergency builders as optional ingredients may also be present as found in WO0034427.

10 The invention will now be further illustrated by way of the following non-limiting examples:

EXAMPLES

15 [(MeN4Py)FeCl]Cl

The ligand N,N-bis(pyridin-2-yl-methyl)-1,1-bis(pyridin-2-yl)-1-aminoethane (MeN4py) was prepared as described in EP 0 909 809 A2.


20 The ligand MeN4Py (33.7 g; 88.5mmoles) was dissolved in 500ml dry methanol. Small portions of FeCl₂.4H₂O (0.95 eq; 16.7 g; 84.0 mmoles) were added, yielding a clear red solution. After addition, the solution was stirred for 30 minutes at room temperature, after which the methanol was
25 removed (rotary-evaporator). The dry solid was ground and 150 ml of ethylacetate was added and the mixture was stirred until a fine red powder was obtained. This powder was washed twice with ethyl acetate, dried in the air and further dried under reduced pressure vacuum at 40 °C. El. Anal. Calc. for
30 [Fe(MeN4py)Cl]Cl.2H₂O: C 53.03; H 5.16; N 12.89; Cl 13.07;

- 28 -

Fe 10.01%. Found C 52.29/ 52.03; H 5.05/5.03; N 12.55/12.61;
Cl: 12.73/12.69; Fe: 10.06/10.01%.

Dimethyl 2,6-di-(2-pyridyl)-1-methyl-piperid-4-one-3,5-


5 dicarboxylate (NPy2) (MW: 383.4 g/mol)



Picolylaldehyde (83.1 mmol; 8 ml) was added drop wise to an ice-bath cooled solution of acetonedicarboxylic acid
10 dimethyl ester (41.55 mmol, 6 ml) in methanol (30 ml), subsequent addition of aqueous (40%) methylamine (41.55 ml, 4.8 ml) yielded an orange red solution. The solution was stirred for 5 min at 0 °C and then cooled to 18 °C. After approximately two days storage at 18 °C large crystals
15 formed in the reaction mixture. The crystals were removed by filtration and washed with cold ethanol and recrystallised from ethanol. Further concentration of the filtrate yielded a further 10% of product. The total yield of the title compound was 12.43 g (78%).
20 ¹H-NMR (CD₂Cl₂) (predominantly enol): 1.70 (s, 3H, -NMe); 3.60; 3.67 (2s, 6H, -OMe); 4.19 (d, J=10Hz, 1H, pipH4); 4.46 (d, J=10Hz, 1H, pipH5); 4.81 (s, 1H, pipH2); 7.10-8.60 (m, 10H, pyHs)

- 29 -

Dimethyl 2,6-di-(2-pyridine)-1-(pyridin-2-ylmethyl)-piperid-
4-one-3,5-dicarboxylate (NPy3) (MW: 460.5 g/mol)



The process for the synthesis of NPy3 is substantially the
5 same as found above for NPy2 except that the following
precursors are used: acetonedicarboxylic acid dimethyl ester
(0.05 mol; 7.2ml); 2-pyridinaldehyde (0.1 mol; 9.56 ml);
and, picolylamine (0.05 ml; 5.1 ml to yield 19.31 g (84%).
¹H-NMR: (DCCl₃) (predominantly enol): 3.55; 3.81 (s, 6H, -
10 OMe); 3.83 (s, 2H, CH₂-py); 4.29 (d, J=12Hz, 1H, pipH4); 4.81
(d, J=12Hz, 1H, pipH5); 4.89 (s, 1H, pipH2); 7.05-7.78 (m,
9H, pyHs); 8.42-8.48 (m, 2H, pyH6, pyH6); 8.62 (d, J=8Hz),
1H, pyH6)

15 Dimethyl 2,4-di-(2-pyridyl) -3,7-dimethyl-3,7-diaza-
bicyclo[3.3.1]nonan-9one-1,5-dicarboxylate (N2Py2) (MW: 438.5
g/mol)

To a suspension of NPy2 (26.1 mmol; 10g) in 80 ml ethanol
was added an aqueous (37%) formaldehyde solution (62.66
20 mmol, 5.64 ml) followed by an aqueous 40% solution of
methylaniline (31.33 ml; 3.6 ml). The reaction mixture was
then heated at reflux for 5 min after which the reaction
mixture was cooled to ambient temperature. After scratching
the inside of the vessel holding the reaction mixture white
25 crystals were formed. After filtration of the crystalline
product, the product was washed with ethanol and the

- 30 -

crystalline product dried under produced pressure to yield 8.61 g (75.3%) of the title compound.

¹H-NMR (CD₂Cl₂): 2.00 (s, 3H, N7-Me); 2.22 (s, 3H, N3-Me); 2.45 (d, J=12Hz, 2H, bisH6ax, bisH8ax); 2.93 (d, J=12Hz, 2H, bisH6eq, bisH8eq); 3.75 (s, 6H, -OMe); 4.67 (s, 2H, bisH2, bisH4); 7.23 (m, 2H, pyH5); 7.80 (t, J=8Hz, 2H, pyH4); 8.07 (d, J=8Hz, 2H, pyH3); 8.49 (d, J=5Hz, 2H, pyH6).

Dimethyl 2,4-di-(2-pyridyl) -3-methyl-7-(pyridin-2-ylmethyl)-3,7-diaza-bicyclo[3.3.1]nonan-9-one-1,5-dicarboxylate (N2Py3o) (MW: 515.22 g/mol)

2-Aminomethyl-pyridine (4.3 g, 39.7 mmol) and formaldehyde (37% in water) (6.5 mL, 79.4 mmol) were added to a suspension of NPy2 (12.71 g, 33.1 mmol) in 200 mL ethanol. The suspension was stirred under reflux for 30 minutes resulting in a clear brown solution. The solvent was removed under reduced pressure and the remaining solid was crystallised from ethanol to yield the title compound as a white solid (4.2 g, 25 %).

¹H-NMR (300 MHz, CDCl₃): 1.94 (s, 3H, N-Me), 2.68 (d, 2H, J=12Hz, bisH6ax, bisH8ax-); 3.14 (d, 2H, J=12Hz, bisH6eq, bisH8eq); 3.57 (s, 2H, CH₂-Py), 3.76 (s, 6H, OMe), 4.66 (s, 2H, bisH2, bisH4), 7.09 (t, 2H, J=1.5Hz, Py-H), 7.21 (t, 1H, J=6.0Hz, Py-H), 7.33 (d, 1H, J=7.6Hz, Py-H), 7.50 (t, 2H, J=1.7Hz, Py-H), 7.66 (t, 1H, J=7.5Hz, Py-H), 7.92 (d, 2H, J=7.8Hz, Py-H), 8.45 (d, 2H, J=4.0Hz, Py-H), 8.62 (d, 1H, J=4.8Hz, Py-H).

- 31 -

Dimethyl 2,4-di-(2-pyridyl)-3-(pyrid-2-ylmethyl)-7-methyl-
3,7-diaza-bicyclo[3.3.1]nonan-9-one-1,5-dicarboxylate
(N2Py3u) (MW: 515.22 g/mol)

To a suspension of NPy3 (21.79 g, 47.3 mmol) in 250 mL
5 ethanol was added aqueous (40%) methylamine (4.8 mL, 56.7
mmol) and aqueous (37%) formaldehyde (9.2 mL, 113.4 mmol).
The suspension was stirred under reflux for 3 h which
resulted in a deep brown solution being formed. The solvent
was removed under reduced pressure and the resulting
10 green/brown solid was recrystallized from ethanol to yield
6.58 g (27 %) of the title compound as a white solid.
¹H-NMR (300 MHz, CDCl₃): 2.20 (s, 3H, N-Me), 2.56 (d, 2H,
J=12Hz, bisH6ax, bisH8ax), 2.98 (d, 2H, J_{HH}=12Hz, bisH6eq,
bisH8eq), 3.72 (s, 8H, OMe, CH₂-Py), 5.42 (s, 2H, bisH2,
15 bisH4), 6.76 (d, 1H, J=7.7Hz, Py-H), 6.97 (t, 1H, J=5.7 Hz,
Py-H), 7.13 (t, 2H, J=6.0Hz, Py-H), 7.38 (t, 2H, J=7.6Hz,
Py-H), 7.68 (t, 2H, J=7.6Hz, Py-H), 8.06 (d, 1H, J=7.6Hz,
Py-H), 8.43 (d, 1H, J=4.6Hz, Py-H), 8.47 (d, 2H, J=4.4Hz,
Py-H).
20 Anal. Calcd for C₂₈H₂₉N₅O₅: C 65.23, H 5.67, N 13.58; found: C
64.86, H 5.60, N 13.41.

Dimethyl 2,4-di-(2-pyridyl) -3,7-bis-(pyridin-2- ylmethyl)-
3,7-diaza-bicyclo[3.3.1]nonan-9-one-1,5-dicarboxylate
25 (N2Py4) (MW: 594.7 g/mol)
To a heated solution of NPy3 (32.61 mmol; 15g) in 25 mL THF
an aqueous (40 %) formaldehyde (78.3 mmol; 7.0 mL) solution
was added drop wise, after which 2-aminomethyl-pyridine
(39.1 mmol; 4 mL) was added drop wise resulting in a dark
30 solution. The mixture was further heated for 1 h at 85 °C.
After the reaction mixture was cooled a greenish precipitate


- 32 -

was formed. The precipitate was then washed with cold ethanol and crystallised from ethanol to yield the title compound, 4.75 g (25%). In some instances no precipitate is formed and in this case it is advisable to remove the THF under reduced pressure to yield a black oil and add 5 ml EtOH. After addition of the EtOH the title compound crystallises out after 3 to 4 hrs.

¹H-NMR (CDCl₃): 2.87 (d, J=12Hz, 2H, bisH6ax, bisH8ax); 3.46 (d, J=12Hz, 2H, bisH6eq, bisH8eq), 3.66-3.71 (m, 10H, -OMe, -CH₂-py); 5.35 (s, 2H, bisH2, bisH4); 6.73-8.63 (m s, 20H, pyHs).


Table 1 exemplifies the structures of ligands of the present invention that were used in bleaching experiments.

pyridin-2-ylmethyl =



15

- 33 -

	Ligand
R3 = R4 = -C(O)OMe R1 = R2 = pyridin-2-ylmethyl	N2Py4
R3 = R4 = -C(O)OMe R1 = R2 = -CH3	N2Py2
R3 = R4 = -C(O)OMe R1 = Me R2 = pyridin-2-ylmethyl	N2Py3u
R3 = R4 = -C(O)OMe R1 = pyridin-2-ylmethyl R2 = Me	N2Py3o

General synthesis of complex from ligand

A solution of 2 mmol metal salt (FeSO₄, FeCl₂, CuCl₂, Fe(ClO₄)₂ etc) in 1 mL methanol was added to a solution of 2
 5 mmol ligand in 1 mL acetonitrile. The clear dark (generally brown for Fe complex and blue for Cu complex) solution was put in a diethylether diffusion bath. After several hours, coloured crystals precipitated from the solution.

10 [FeSO₄(N2Py3o)]

(Dimethyl 2,4-di-(2 pyridyl) -3-methyl-7-(pyridin-2-ylmethyl)-3,7-diaza-bicyclo[3.3.1]nonan-9-one-1,5-dicarboxylate)sulfatoiron(II) [C₂₈H₂₉FeN₅O₉S M = 667,13g/mol]

- 34 -

Anal. Calcd for $C_{28}H_{29}FeN_5O_9S$: C 47.80, H 4.73, N 9.96; found
+2H₂O: C 47.16, H 4.91, N 9.84. FAB⁺MS(nitrobenzylalcohol):
686.1 (MH⁺+H₂O)

5 [FeSO₄(N2Py3u)]

((Dimethyl-2,4-di-(2-pyridyl)-3-(pyridin-2-ylmethyl)-7-
methyl-3,7-diaza-bicyclo[3.3.1]nonan-9-one-1,5-
dicarboxylate)sulfatoiron(II) (M = 667,13g/mol)

Anal. Calcd for $C_{28}H_{29}FeN_5O_9S$: C 46.61, H 4.89, N 9.71; found
10 +3H₂O: C 47.27, H 4.81, N 9.88. FAB⁺MS(nitrobenzylalcohol):
686.1 (MH⁺+H₂O)

[FeCl(N2Py3o)]Cl

Chloro(dimethyl 2,4-di-(2-pyridyl) -3-methyl-7-(pyridin-2-
15 ylmethyl)-3,7-diaza-bicyclo[3.3.1]nonan-9-one-1,5-
dicarboxylate)iron(II)- chloride hydrate Anal. Calcd for
 $C_{28}H_{29}Cl_2FeN_5O_5$: C 49.58, H 4.90, N 10.45; found +2H₂O: C 49.45,
H 4.79, N 10.00. FAB⁺MS(nitrobenzylalcohol): 624.1
[FeCl(N2Py3o)·H₂O]

20

[Fe(N2Py4)]Cl₂

(Dimethyl-2,4-di-(2-pyridyl)-3,7-bis-(pyridin-2-ylmethyl)-
3,7-diaza-bicyclo[3.3.1]nonan-9-one-1,5-
dicarboxylate)iron(II)- dichloride hydrate [$C_{33}H_{38}Cl_2FeN_6O_6$ M =
25 741.44g/mol], Anal. Calcd for $C_{33}H_{38}Cl_2FeN_6O_6$: C 53.75, H 4.65,
N 11.40; found: C 53.20, H 4.74, N 11.22.
FAB⁺MS(Nitrobenzylalcohol): 683.1 [Fe (N2Py4)·H₂O]

- 35 -

[Fe(NCCH₃)₂(triflate)₂]

The following reaction was performed under anhydrous conditions under argon using standard Schlenck/cannular techniques.

5

To a cooled stirred mixture of iron powder (5.6 g, 0.1 mol) in acetonitrile (60 ml) trifluoromethanesulfonic acid (0.2 mol, 17.7 ml) was added. After addition, the reaction mixture was heated for 45 min at 90 °C. The reaction mixture was cooled, after which remaining solid material was filtered off. To the remaining solution 40 ml of diethyl ether was slowly added resulting in a white precipitate. The white precipitate was filtered off under argon, and washed with 20 ml of ether. The hygroscopic material was stored under. Yield 31.7% (13.8g).

[Fe(N₂Py₂)(triflate)₂] (MW: 792.46 g/mol)

In a water-free system, 0.23 mmol (100 mg) of [Fe(CH₃CN)₂(triflate)₂] and ligand (0.23 mmol; 100 mg) in dry acetonitrile is added. Via slow diffusion of ether into this solution, the crystals with the iron complex are formed. The yield for this procedure is typically 50%. Anal. Calcd for FeC₂₅H₂₉N₄O₁₁S₂F₆ calc 38.91, H 3.51, N 8.40; found: C 38.86, H 3.41, N 8.32.

Bleaching Experiments

Bleaching results obtained on tomato stains for the different complexes (10 µM) or preformed ligand/iron species (by premixing 2 mM ligand/1mM iron perchlorate in ethanol/water (1/1). The tomato stains were washed with the LAS/buffer system (0.6 g/L NaLAS in 10 mM carbonate buffer)

30

- 36 -

for 30 min at 30 °C in a bottle containing 25 ml of the wash solution. After the wash, cloths were washed with water and dried in a tumble drier till dryness.

5 The reflectance measurements were obtained using a Minolta™ 3700d spectrophotometer at 460 nm. The difference in reflectance before and after the wash is defined as a ΔR_{460} value. The bleaching results obtained immediately after drying ($t=0$) are shown. All values expressed in $\Delta \Delta R_{460}$
 10 values (blank, LAS only subtracted); typical errors are in the order of 2 points. A higher value means a better bleaching performance.

Table 2: Bleaching results ($\Delta \Delta R_{460}$) on tomato oil of the
 15 preformed complexes and ligand/iron salt mixtures (active).

Table 2

Active	t=0
N2Py4+Fe(II)	10
[Fe(N2py3o)Cl]Cl	24
[Fe(N2py3u)SO4]	22
N2py3u +Fe(II)	11
N2py3o +Fe(II)	20
[Fe(N2py2)Cl ₂]	7
N2py2 + Fe(II)	1

The results in Table 2 show the following:

20 A good bleaching activity is obtained on tomato oil stains with especially the iron complexes containing N2Py3 ligands (u and o) and to a lesser extent the N2py4 ligand/iron

- 37 -


mixture in air bleaching. In all cases the bleaching results are significantly better than the N2py2-containing systems (either Fe complex or ligand/iron salt mixture). It is noteworthy that the ligand in combination with iron salt is
5 effective in air bleaching.

- 38 -

CLAIMS:

1. A bleaching composition comprising:

- 5 a) a monomer ligand or transition metal catalyst thereof of a ligand having the formula (I):



- 10 wherein each R is independently selected from: hydrogen, F, Cl, Br, hydroxyl, C1-C4-alkyl-O-, -NH-CO-H, -NH-CO-C1-C4-alkyl, -NH2, -NH-C1-C4-alkyl, and C1-C4-alkyl; R1 and R2 are independently selected from: C1-C4-alkyl,
- 15 C6-C10-aryl, and, a group containing a heteroatom capable of coordinating to a transition metal, wherein at least one of R1 and R2 is the group containing the heteroatom; R3 and R4 are independently selected from hydrogen, C1-C8 alkyl, C1-C8-alkyl-O-C1-C8-alkyl, C1-C8-alkyl-O-C6-C10-aryl,
- 20 C6-C10-aryl, C1-C8-hydroxyalkyl, and $-(CH_2)_nC(O)OR_5$ wherein R5 is independently selected from: hydrogen, C1-C4-alkyl, n is from 0 to 4, and mixtures thereof; and, X is selected from C=O, $-[C(R_6)_2]_y-$ wherein Y is from 0 to 3
- 25 each R6 is independently selected from hydrogen, hydroxyl, C1-C4-alkoxy and C1-C4-alkyl; and,

- 39 -

b) the balance carriers and adjunct ingredients.

2. A bleaching composition according to claim 1, wherein R1 and R2 are both selected from a group containing a heteroatom capable of coordinating to a transition metal.

3. A bleaching composition according to any preceding claim, wherein the group containing the heteroatom is:
a heterocycloalkyl: selected from the group consisting of:
pyrrolinyl; pyrrolidinyl; morpholinyl; piperidinyl;
piperazinyl; hexamethylene imine; 1,4-piperazinyl;
tetrahydrothiophenyl; tetrahydrofuranlyl; tetrahydropyranlyl;
and oxazolidinyl, wherein the heterocycloalkyl may be connected to the ligand via any atom in the ring of the selected heterocycloalkyl,
a -C1-C6-alkyl-heterocycloalkyl, wherein the heterocycloalkyl of the -C1-C6-heterocycloalkyl is selected from the group consisting of: piperidinyl; piperidine; 1,4-piperazine, tetrahydrothiophene; tetrahydrofuran;
pyrrolidine; and tetrahydropyran, wherein the heterocycloalkyl may be connected to the -C1-C6-alkyl via any atom in the ring of the selected heterocycloalkyl,
a -C1-C6-alkyl-heteroaryl, wherein the heteroaryl of the -C1-C6-alkylheteroaryl is selected from the group consisting of: pyridinyl; pyrimidinyl; pyrazinyl; triazolyl;
pyridazinyl; 1,3,5-triazinyl; quinolinyl; isoquinolinyl;
quinoxalinyl; imidazolyl; pyrazolyl; benzimidazolyl;
thiazolyl; oxazolidinyl; pyrrolyl; carbazolyl; indolyl; and isoindolyl, wherein the heteroaryl may be connected to the -C1-C6-alkyl via any atom in the ring of the selected

- 40 -

heteroaryl and the selected heteroaryl is optionally substituted by -C1-C4-alkyl,

a C0-C6-alkyl-phenol or thiophenol,

a C2-C4-alkyl-thiol, thioether or alcohol,

5 a C2-C4-alkyl-amine, and

a C2-C4-alkyl-carboxylate.

4. A bleaching composition according to any preceding claim, wherein: each R is the same; and $R_3 = R_4$.

10

5. A bleaching composition according to any preceding claim, wherein R_3 and R_4 are the same and are $-(CH_2)_nC(O)O-C1-C4-alkyl$.

15 6. A bleaching composition according to any preceding claim, wherein R_3 and R_4 are selected from the group consisting of CH_2OH , $-C(O)O-C1-C6-alkyl$, and phenyl.

7. A bleaching composition according to any proceeding
20 claim, wherein at least one R_1 and R_2 is a 3-C0-C6-alkyl-pyridin-2-yl-C0-C6-alkyl.

8. A bleaching composition according to any preceding claim, wherein $Y = 1$

25

9. A bleaching composition according to any preceding claim, wherein R_3 and R_4 are $-C(O)O-C1-C6-alkyl$.

10. A bleaching composition according to any preceding
30 claim, wherein at least one of R_1 and R_2 is selected from the group consisting of: 3-ethyl-pyridin-2-ylmethyl,

- 41 -

pyridin-2-ylmethyl, 3-methyl-pyridin-2-ylmethyl, and 6-amide-pyridin-2-ylmethyl.

11. A bleaching composition according to claim 10, wherein
5 at least one of R1 and R2 is pyridin-2-ylmethyl.

12. A bleaching composition according to any preceding
claim, wherein both R1 and R2 are pyridin-2-ylmethyl and R
is H.

10

13. A bleaching composition according to any preceding
claim, wherein X is C=O.

14. A bleaching composition according to any preceding
15 claim, wherein the bleaching composition comprises the free
ligand.

15. A bleaching composition according to claims 1 to 12,
wherein the complex is of the general formula (A1):

20



in which:

M represents a metal selected from Mn(II)-(III)-(IV)-
25 (V), Cu(I)-(II)-(III), Fe(II)-(III)-(IV)-(V), Co(I)-(II)-
(III), Ti(II)-(III)-(IV), V(II)-(III)-(IV)-(V), Mo(II)-
(III)-(IV)-(V)-(VI) and W(IV)-(V)-(VI);

X represents a coordinating species selected from any
mono, bi or tri charged anions and any neutral molecules
30 able to coordinate the metal in a mono, bi or tridentate
manner;

- 42 -

Y represents any non-coordinated counter ion;
a represents an integer from 1 to 10;
k represents an integer from 1 to 10;
n represents an integer from 1 to 10;
5 m represents zero or an integer from 1 to 20; and
L represents a ligand as defined in claims 1 to 12, or
its protonated or deprotonated analogue.

16. A bleaching composition according to claim 15, wherein
10 M represents a metal selected from Fe(II)-(III)-(IV)-(V).

17. A bleaching composition according to claim 16, wherein
M represents a metal selected from Fe(II) and Fe(III).

15 18. A ligand of formula (I) according to claim 1 or a
transition metal catalyst thereof with the proviso that the
following compounds are excluded:
dimethyl 2,4-di-(2-pyridyl)-3,7-bis-(pyridin-2-ylmethyl)-
3,7-diaza-bicyclo[3.3.1]nonan-9-one-1,5-dicarboxylate;
20 1,5-bis-(hydroxymethylene)-2,4-di-(2-pyridyl)-3,7-bis-
(pyridin-2-ylmethyl)-3,7-diazabicyclo[3.3.1]nonan-9-ol;
dimethyl 2,4-di-(2-pyridyl)-3,7-bis-(pyridin-2-ylethyl)-3,7-
diaza-bicyclo[3.3.1]nonan-9-one-1,5-dicarboxylate;
dimethyl 2,4-di-(2-pyridyl)-3-(5-carboxypentyl)-7-methyl-
25 3,7-diaza-bicyclo[3.3.1]nonan-9-one-1,5-dicarboxylate;
dimethyl 2,4-di-(2-pyridyl)-3-(2-methoxyethyl)-7-methyl-3,7-
diaza-bicyclo[3.3.1]nonan-9-one-1,5-dicarboxylate; diethyl-
2,4-dipyridyl-7-picolyl-3,7-diaza-bicyclo-[3.3.1]-nonan-9-
one-1,5-dicarboxylate ; diethyl-2,4-dipyridyl-7-benzyl-3-
30 hydroxyethyl-3,7-diaza-bicyclo-[3.3.1]-nonan-9-one-1,5-
dicarboxylate; and, dimethyl-2,4-dipyridyl-7-benzyl-3-

- 43 -

hydroxyethyl-3,7-diaza-bicyclo-[3.3.1]-nonan-9-one-1,5-dicarboxylate.

19. A ligand of formula (I) according to claim 18 or a
5 transition metal catalyst thereof, wherein at least one of
R1 or R2 is pyridin-2-ylmethyl and the other is selected
from CH3, -C2H5, -C3H7, and -C4H9.
20. A perchlorate salt of dimethyl 2,4-di-(2-pyridyl) -3,7-
10 di(pyridin-2-ylmethyl)-3,7-diaza-bicyclo[3.3.1]nonan-9-one-
1,5-dicarboxylate (N2Py4).

INTERNATIONAL SEARCH REPORT

International Application No.

PCT/EP 01/13314

A. CLASSIFICATION OF SUBJECT MATTER

IPC 7 C11D3/16 C11D3/39 C07D471/08 C07D487/04 C07D487/08
 //(C07D471/08,223:00,221:00),(C07D487/04,209:00,209:00),
 (C07D487/08,223:00,223:00),(C07D487/08,245:00,225:00)

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 7 C11D C07D

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

EPO-Internal, CHEM ABS Data

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	R. HALLER: "Zur Kenntnis substituierter 3,7-Diaza- und 3-Oxa-7-aza-bicyclo-'3.3.1!-nonanone" ARZNEIMITTEL FORSCH., vol. 15, no. 11, 1965, pages 1327-1330, XP002196150	18
A	Table 1: compounds VI, VII and X	19,20
	Table 2: compounds XVIII, XIX and XX	
A	U. KUHLE ET AL.: "Diazabicyclo-'3.3.1!nonanone-type Ligands for the Opioid Receptors" ARCH. PHARM., vol. 333, no. 7, 2000, pages 226-230, XP002196151	18
	Table 1: Compounds 13-17	
	--- -/--	



Further documents are listed in the continuation of box C.



Patent family members are listed in annex.

* Special categories of cited documents:

A document defining the general state of the art which is not considered to be of particular relevance

E earlier document but published on or after the international filing date

L document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

O document referring to an oral disclosure, use, exhibition or other means

P document published prior to the international filing date but later than the priority date claimed

T later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

X document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

Y document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

G document member of the same patent family

Date of the actual completion of the international search

23 April 2002

Date of mailing of the international search report

15/05/2002

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
 NL - 2280 HV Rijswijk
 Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
 Fax: (+31-70) 340-3016

Authorized officer

Neys, P

INTERNATIONAL SEARCH REPORT

International Application No

PCT/EP 01/13314

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	H. BÖRZEL ET AL.: "Stabilization of Copper Dioxygen Compounds: Design, Synthesis, and Characterization" CHEM. EUR. J., vol. 5, no. 6, 1999, pages 1716-1721, XP002196152 cited in the application Page 1719 - Scheme 2: compound L2 -----	18
A	WO 00 60045 A (PROCTER & GAMBLE) 12 October 2000 (2000-10-12) cited in the application the whole document -----	1-20

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/EP 01/13314

Patent document cited in search report		Publication date		Patent family member(s)		Publication date
WO 0060045	A	12-10-2000	AU	4061900 A		23-10-2000
			WO	0060045 A1		12-10-2000
<hr/>						

